

1%	3%	Product Name
		Aditan Milling Yellow R
		Aditan Golden Yellow R
		Aditan Orange 2G
		Aditan Orange GL
		Aditan Fast Orange OS
		Aditan Scarlet R / Red MG
		Aditan Scarlet 6B
		Aditan Red NB


1%	3%	Product Name
		Aditan Bordeaux BV
		Aditan Blood Red
		Aditan Royal Blue
		Aditan Brilliant Blue F
		Aditan Dark Blue N / LSB
		Aditan Blue S5R
		Aditan T. Blue A
		Aditan Green V

1%	3%	Product Name
		Aditan Olive Green PVV
		Aditan Dark Green LS
		Aditan Grey MB
		Aditan Beige T01
		Aditan Beige E
		Aditan Havana Brown
		Aditan Brown CGG
		Aditan Brown HH

1%	3%	Product Name
		Aditan Brown EGB / CR
		Aditan Brown Y2R
		Aditan Brown CG
		Aditan Brown SG
		Aditan Tobacco Brown
		Aditan Brown NT
		Aditan Brown GB
		Aditan Olive Brown

1%	3%	Product Name
		Aditan Brown GRL
		Aditan Brown RL
		Aditan Brown AN
		Aditan Brown MFR
		Aditan Brown 2R
		Aditan Brown P3R
		Aditan Brown N2R
		Aditan Brown HBR

1%	3%	Product Name
		Aditan Brown SR / N
		Aditan Brown M
		Aditan Brown CFB / SGR
		Aditan Dark Brown SP
		Aditan Black MCLI
		Aditan Black SP
		Aditan Jet Black
		Aditan Black NT



## COMPANY PROFILE

### Overview :

- Inception : 2007
- Manufacturing Plants : 4 nos.
- Manufacturing Capacity : 5000 MT / Annum (Crude)
- RO Plant for Salt-Free Dyestuff.
- 1 R & D Lab
- 2 Q/C Lab. with all latest testing instruments i.e. UV Scanner, Spectra Photometer, Leather Dyeing M/c., Light Chamber, PVC Migration Testing, Perspiration Fastness Testing etc.

Application Method				
Raw Material : Full Chrome wet blue cow leather, % is based on Shaved weight				
Process	%	Product	Notes	Time
Acid Wash	400% 0.5% 1.0%	Water Acetic Acid Wetting Agent		45'
Bleaching	200% 0.5% + 1.0% + 1.5% + 2.0%	Water Formic Acid KMnD4 (Pot. Permananta) Sodium Bi Sulphate Oxalic Acid		- 10' 30' 20' 30'
Rechroming	100% 4% 2% + 1% + 100% + 1.5% 1.0% + 3%	Water Chrome Powder Chrome Syntan Fish Oil Water Sodium Sodium Bi Carbonate ZY/540		- - - 30' 30' 30' 3x10' 30' 30'
Neutralisation	200% 0.5% + 2.0%	Water Ammonium Bi Carbonate Sellasol NG		- 15' 45'
Retanning Light Shade / Dark Shade	200% + 2% + 3% 3% 3% 3% + 3%	Water / Water Lip. Liq. 2FB / ASN Relusan Re / RE DI / OS DLE / DCD FB6 / R7 VW (White Veg) / GS Powder Dye - X% / Dye - X%		- 20' 20' - - - 40'
Fatiquorine	+ 3% 3% 3% 3% + 3%	ASN SAF 2FB HQ Formic Acid		- - - - 45' 2x10'

Methods & Properties recommended herein are based on the present state of our knowledge and is intended to serve only as a guide to customers in the use of our products, without any obligation on our part. It does not release customers from obligation to check it's validity and to test our products as per their suitability.

No.	Product	Solubility IUF-201	Fastness			PVC Migration (IUF-442)
			Light (IUF-402)	Washing (IUF-423)	Perspiration (IUF-426)	
1	Aditan Milling Yellow R	50	3-4	4	4-5	3
2	Aditan Golden Yellow R	50	3-4	4	4	3-4
3	Aditan Orange 2G	60	3	2	2-3	2
4	Aditan Orange GL	50	4-5	3	3	3-4
5	Aditan Fast Orange OS	50	3	4	3-4	3
6	Aditan Scarlet R / Red MG	40	3	4	3	3
7	Aditan Scarlet 6B	50	3	3-4	3-4	3
8	Aditan Red NB	40	4	3-4	2-3	3
9	Aditan Bordeaux BV	50	4	3-4	4	3
10	Aditan Blood Red	50	3	4	3	3
11	Aditan Royal Blue	70	2-3	4	3	2-3
12	Aditan Brilliant Blue F	50	3	3-4	3	3
13	Aditan Dark Blue N / LSB	50	4	4	4	4
14	Aditan Blue SSR	50	4-5	4	2	3-4
15	Aditan T. Blue A	80	3-4	3	2-3	3
16	Aditan Green V	50	3	3	4-5	3-4

No.	Product	Solubility IUF-201	Fastness			PVC Migration (IUF-442)
			Light (IUF-402)	Washing (IUF-423)	Perspiration (IUF-426)	
17	Aditan Olive Green PW	60	4	4-5	2-3	3-4
18	Aditan Dark Green LS	50	3-4	3-4	3-4	4
19	Aditan Grey MB	60	4	3-4	3-4	4
20	Aditan Beige T01	60	3-4	4	2-3	3
21	Aditan Beige E	70	4	4	2-3	4
22	Aditan Havana Brown	60	4	4-5	3-4	3
23	Aditan Brown CCG	60	3	3-4	2-3	3-4
24	Aditan Brown HH	70	4	4	4-5	4
25	Aditan Brown EGB / CR	60	5	3-4	3	3-4
26	Aditan Brown Y2R	50	4-5	4	3-4	3
27	Aditan Brown CG	60	4-5	4	3	3-4
28	Aditan Brown SG	50	4	2-3	3	4
29	Aditan Tobacco Brown	50	4-5	4	3	4
30	Aditan Brown NT	50	4	3-4	3	3-4
31	Aditan Brown GB	45	4	2-3	3	3-4
32	Aditan Olive Brown	50	4	3	3-4	4-5

No.	Product	Solubility IUF-201	Fastness			PVC Migration (IUF-442)
			Light (IUF-402)	Washing (IUF-423)	Perspiration (IUF-426)	
33	Aditan Brown GR1	60	4	3-4	3	3-4
34	Aditan Brown RL	50	4-5	3-4	3-4	4
35	Aditan Brown AN	50	3-4	3	3-4	3
36	Aditan Brown MFR	45	4	3-4	3	3-4
37	Aditan Brown 2R	60	4-5	3-4	3	3-4
38	Aditan Brown P3R	55	4	3	3-4	3-4
39	Aditan Brown M2R	50	3	2-3	4	4-5
40	Aditan Brown HBR	60	3-4	3-4	2-3	3-4
41	Aditan Brown SR / N	50	3-4	3	2-3	3
42	Aditan Brown M	60	4-5	4	3	2-3
43	Aditan Brown CFB / SGR	60	3-4	4	3-4	3-4
44	Aditan Dark Brown SP	50	3-4	3-4	3	3-4
45	Aditan Black MCLI	60	4	4	3-4	4-5
46	Aditan Black SP	60	4	4	3	4
47	Aditan Jet Black	70	4	4	3-4	4-5
48	Aditan Black NT	70	4	4	3-4	4-5



**ADITYA**  
COLOR CHEM  
LET THE COLOR TALK

**Mfg. & Exporter of S.O. Dyes**

An ISO 9001:2015 Certified Company  
Government of India Certified Star Export House



### GROUP OF COMPANIES

- Aditya Color Chem
- Aditya Dyestuff Industries
- Aditya Dye Chem
- Aaditya Dyechem Private Limited
- A. S. Industries
- Vibrant Colors

(O) : +91 79 4008 3150 (M) : +91 98799 87967  
adityachem2001@gmail.com • info@adityachem.com  
www.adityachem.com